

Panel 755

Un-faced semi-rigid slab of volcanic stone wool.



Application

Used for acoustic insulation in general building applications.

Technical Properties

| Property | Description | | Standard |
|--|----------------|---|------------|
| Nominal density (kg/m ³) | 145 | | EN 1602 |
| Thermal conductivity W/(m*K) | 0,039 | | EN 12667 |
| Dimensions (mm) | 1200 x 600 | | |
| Fire reaction /Euroclass | A1 | | EN 13501.1 |
| Thermal resistance (m ² K/W) | Thickness (mm) | Thermal resistance (m ² K/W) | |
| | 30 | 0.75 | |
| | 50 | 1.25 | |
| Thickness tolerance (mm) | T3 | | EN 823 |
| Dimensional stability at a specific temperature and humidity | DS (70,90) | | EN 1604 |
| Water vapour transmission | MU1 | ($\mu = 1$) | EN 12086 |
| Short term water absorption (kg/m ²) | WS | (< 1,0 kg/m ²) | EN 1609 |
| Long term water absorption by partial immersion (kg/m ²) | WL(P) | (< 3,0 kg/m ²) | EN 12086 |

Advantages

- Fast and easy to install.
- Maximum security in case of fire.
- Well-known improvement of the sound and thermal insulation.
- Neither-hydrophilic nor hygroscopic.
- Chemically inert.
- Environmental Product Declaration
- Free of CFC and HCFC, respectful with the environment.
- Low emissions certificate



Apr-22

ROCKWOOL Peninsular S.A.U.
Ctra. Zaragoza, Km. 53,5 N121.
31380 Caparroso, Navarra, Spain
T (+34)902 430 430
www.rockwool.es