

# Rockbardage Solape Derecho

Un-faced semi-rigid stone wool slab with a gap that allows its precise adaptation to the right overlap metal tray. Thermal bridge breaking of 40 mm.



## Application

Thermal and acoustic insulation in external vertical metal walls of industrial buildings, for right overlap metal trays.

## Technical Properties

Property	Description			Standard
Nominal density (kg/m <sup>3</sup> )	50			EN 1602
Thermal conductivity W/(m*K)	0,033			EN 12667
Dimensions (mm)	1350 x 400 / 1350 x 450 / 1350 x 500 / 1350 x 600			
Fire reaction /Euroclass	A1			EN 13501.1
Thermal resistance (m <sup>2</sup> K/W)	Thickness (mm)	Thermal resistance (m <sup>2</sup> K/W)	Thickness (mm)	Thermal resistance (m <sup>2</sup> K/W)
	130	3.90	190	5.75
	140	4.20	197	5.95
	170	5.15		
Thickness tolerance (mm)	T5			EN 823
Dimensional stability at a specific temperature and humidity	DS (70,90)			EN 1604
Air flow resistivity	AF15	( > 15 KPa · s/m <sup>2</sup> )		EN 29053
Water vapour transmission	MU1	( $\mu = 1$ )		EN 12086
Short term water absorption (kg/m <sup>2</sup> )	WS	( < 1,0 kg/m <sup>2</sup> )		EN 1609
Long term water absorption by partial immersion	WL(P)	( < 3,0 kg/m <sup>2</sup> )		EN 12087

## Advantages

- Superior thermal and acoustic performance in metal façade
- Perfect fitting and finishing of the installed product.
- Aesthetic finishing coating of the façade.
- Fast and easy to install.
- Maximum security in case of fire.
- Neither-hydrophilic nor hygroscopic.
- Chemically inert.
- Environmental Product Declaration
- Low emissions certificate



Jun-22

**ROCKWOOL Peninsular S.A.U.**  
Ctra. Zaragoza, Km. 53,5 N121.  
31380 Caparroso, Navarra, Spain  
T (+34)902 430 430  
[www.rockwool.es](http://www.rockwool.es)